

# CONSTRUCTION INDUSTRY

Ref	Type	PH	Viscosity (Poise)	Solids $\pm 1\%$	MFFT $\pm 1^\circ\text{C}$	Recommended For
<b>Styrene Acrylic Emulsions:</b>						
<b>JIFTEX</b> J457	ST/AC	6.5 – 7.5	10 – 40	57	0	Binder: for cementitious flexible waterproof & roof coatings, bonding agent, etc.
<b>JIFTEX</b> J488	ST/AC	8.5 – 9.5	0.5 – 2	47	15	Binder: for cementitious coatings, modification of cement mortar, etc; To increase the flexibility and compressive strength.

**PVA:** Polyvinyl Acetate

**VAM/VV:** Vam Veova

**VAM/VV/AC:** Vam Veova Acrylic

**ST/AC:** Styrene Acrylic

**AC:** Acrylic